

Ax-Tile Axminster Specification

Carpet Width	0.88m x 0.88m
Construction	Traditional Woven Axminster Carpet Tile
Yarn	Dewsbury 3/37's
Pile Content	80% Wool, 20% Nylon
Weft	Polypropylene
Warp	Polyester
Backing	Fray Resistant Latex Compound

		Bitumen Backed			Comfort and Bitumen Backed		
	Quality Name	Gold 3/37's	Platinum 3/37's	Diamond 3/37's	Gold 3/37's	Platinum 3/37's	Diamond 3/37's
	Quality Row	8	9	10	8	9	10
	Pitch	7	7	7	7	7	7
BS ISO 8543	Total Mass (g/m ²)	5415	5680	5940	5030	5345	5660
	Total Mass (oz/yd ²)	191	200.4	209.5	177.4	188.5	199.7
	Total Pile Mass (g/m ²)	1490	1685	1875	1490	1685	1875
	Total Pile Mass (oz/yd ²)	52.6	59.4	66.1	52.6	59.4	66.1
	Surface Pile Mass (g/m ²)	1200	1350	1500	1200	1350	1500
ISO 1765	Total Thickness (mm)	12.5	12.5	12.5	17.3	17.3	17.3
BS ISO 1766	Surface Pile Thickness (mm)	7.8	7.8	7.8	7.8	7.8	7.8
BS ISO 8543	Surface Pile Density (g/cm ³)	0.15	0.165	0.18	0.15	0.165	0.18
ISO 1763	S (per 100mm)	31.5	35.4	39.4	31.5	35.4	39.4
	G (per 100mm)	27.6	27.6	27.6	27.6	27.6	27.6
	Nz/dm ²	868	977	1085	868	977	1085
EN1307:2005	Luxury Class	5	5	5	5	5	5

E.U Standards

Class 33 - Commercial General (EN 1307:2005)



Castor Chair Suitability - Rating A: Continuous use (EN 1307:2005)



Light Fastness (EN 1307:2005)



Slip Resistance No Performance Determined (EN 14041:2005)



Formaldehyde Emission - Classed With Testing (EN 14041:2005)



Resistance to Fraying (EN 1307)



Reaction to Fire: Bfl - s1 (EN 13501-1:2002)



Dimension Stability (EN 1307:2005)



Electrical Behaviour (Body Voltage) (EN ISO 6356)



All specifications subject to normal manufacturing tolerances. Production dye can vary in colour from batch to batch. Cut-pile carpets, may show shading/pile reversal.