

# Fast Track Axminster Specification

Carpet Width	3.66m
Construction	Traditional Woven Axminster
Yarn	Dewsbury 3/37's
Pile Content	80% Wool, 20% Nylon
Weft	Polypropylene
Warp	Polyester
Backing	Fray Resistant Latex Compound

	Quality Name	<b>Bronze 3/37's</b>	<b>Silver 3/37's</b>	<b>Gold 3/37's</b>	<b>Platinum 3/37's</b>	<b>Diamond 3/37's</b>
	Quality Row	6	7	8	9	10
	Pitch	7	7	7	7	7
BS ISO 8543	Total Mass (g/m <sup>2</sup> )	2518	2664	2811	2958	3275
	Total Mass (oz/yd <sup>2</sup> )	74	78.5	82.8	87.2	91.56
	Total Pile Mass (g/m <sup>2</sup> )	1119	1312	1490	1685	1875
	Total Pile Mass (oz/yd <sup>2</sup> )	33.0	38.7	43.9	49.7	55.3
	Surface Pile Mass (g/m <sup>2</sup> )	886	985	1084	1183	1282
ISO 1765	Total Thickness (mm)	11	11	11	11	11
BS ISO 1766	Surface Pile Thickness (mm)	7	7	7	7	7
BS ISO 8543	Surface Pile Density (g/cm <sup>3</sup> )	0.12	0.135	0.15	0.165	0.18
ISO 1763	S (per 100mm)	23.6	27.6	31.5	35.4	39.4
	G (per 100mm)	27.6	27.6	27.6	27.6	27.6
	Nz/dm <sup>2</sup>	651	762	868	977	1085
EN1307:2005	Luxury Class	4	4	5	5	5

## E.U Standards

Class 33 - Commercial General (EN 1307:2005)



Castor Chair Suitability - Rating A: Continuous use (EN 1307:2005)



Light Fastness (EN 1307:2005)



Slip Resistance No Performance Determined (EN 14041:2005)



Formaldehyde Emission - Classed With Testing (EN 14041:2005)



Resistance to Fraying (EN 1307)



Reaction to Fire: Bfl - s1 (EN 13501-1:2002)



All specifications subject to normal manufacturing tolerances. Production dye can vary in colour from batch to batch. Cut-pile carpets, may show shading/pile reversal.